


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C07D 487/04, C09K 19/34 // (C07D 487/04, 209:00, 209:00)		A1	(11) International Publication Number: WO 98/25927
			(43) International Publication Date: 18 June 1998 (18.06.98)
(21) International Application Number: PCT/EP97/06641		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 28 November 1997 (28.11.97)			
(30) Priority Data: 3026/96 10 December 1996 (10.12.96) CH			
(71) Applicant: CIBA SPECIALTY CHEMICALS HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH).			
(72) Inventors: HAO, Zhimin; Route du Centre 19, CH-1723 Marly (CH). IQBAL, Abul; La Dey 202, CH-1732 Arconciel (CH). TEBALDI, Nancy; Chemin des Glycines 6, CH-1753 Matran (CH). PRAEFCKE, Klaus; Kranzallee 62, D-14055 Berlin (DE).		<p>Published</p> <p>With international search report.</p> <p>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</p>	

(54) Title: LIQUID CRYSTALLINE DIKETOPYRROLOPYRROLES

(57) Abstract

A compound of formula (I), wherein B and D are each independently of the other C₆-C₂₄alkyl, (a) or (b), L is (c), (d), (e), (f) or C₁-C₃₇alkyl, R₁ is C₄-C₁₈alkyl, R₂ is hydrogen, C₁-C₄alkyl, C₁-C₄alkoxy, halogen, cyano or nitro, R₃, R₄ and R₅ are each independently of one another hydrogen, OR₆, SR₆, SeR₆, -NHR₆, -NR₆R₇, (g), (h), (i), (j), (k), (l), (m) or (n), with the proviso that at least one of R₃, R₄ and R₅ is not hydrogen, R₆ is C₇-C₃₇alkyl, C₇-C₃₇alkylene or C₅-C₁₈alkyl which is interrupted by 1 to 6 hetero atoms selected from the group consisting of O, S and N, R₇ is hydrogen or R₉, R₈ is hydrogen or C₁-C₄alkyl, and R₉ is C₁-C₁₂alkyl, C₂-C₁₂alkylene or C₃-C₁₂alkyl which is interrupted by 1 to 6 hetero atoms selected from the group consisting of O, S and N. The inventive compounds are distinguished by their liquid crystalline character.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Liquid crystalline diketopyrrolopyrroles

The present invention relates to novel liquid crystalline N-substituted 1,4-diketo-3,6-diarylpyrrolo[3,4-c]pyrroles, 1,4-diketo-3,6-dialkylpyrrolo[3,4-c]pyrroles and 1,4-diketo-3-alkyl-6-arylpyrrolo[3,4-c]pyrroles.


1,4-Diketopyrrolo[3,4-c]pyrroles, including the 1,4-diketo-3,6-dialkylpyrrolo[3,4-c]pyrroles disclosed in US-4,659,775, have been known for some years as excellent pigments.

N-substituted 1,4-diketopyrrolo[3,4-c]pyrroles, which are excellently suitable as pigments, are disclosed in US-4,585,878.

However, except in very rare cases liquid crystalline compounds, such as the phthalocyanine described in J. Amer. Chem. Soc. 104, 5245-5247 (1982), are colourless and must be used together with chromophoric substances to give coloured liquid crystalline phases.


Novel coloured N-substituted 1,4-diketopyrrolo[3,4-c]pyrroles have now been found which, very surprisingly, have a liquid crystalline character.

Accordingly, this invention relates to a compound of formula



wherein

B and D are each independently of the other C₆-C₂₄alkyl,  or




L is $-\text{CO}-\text{C}_6\text{H}_4-\text{R}_1$, $-\text{C}_6\text{H}_4-\text{R}_1$, $-\text{C}_6\text{H}_4-\text{OR}_1$, $-\text{C}_6\text{H}_4-\text{SR}_1$ or

$\text{C}_1\text{-C}_{37}\text{alkyl}$,

R_1 is $\text{C}_4\text{-C}_{18}\text{alkyl}$,

R_2 is hydrogen, $\text{C}_1\text{-C}_4\text{alkyl}$, $\text{C}_1\text{-C}_4\text{alkoxy}$, halogen, cyano or nitro,

R_3 , R_4 and R_5 each independently of one another hydrogen, OR_6 , SR_6 , SeR_6 , $-\text{NHR}_6$, $-\text{NR}_6\text{R}_7$,



with the proviso that at least one of R_3 , R_4 and R_5 is not hydrogen,

R_6 is $\text{C}_7\text{-C}_{37}\text{alkyl}$, $\text{C}_7\text{-C}_{37}\text{alkylene}$, or $\text{C}_5\text{-C}_{18}\text{alkyl}$ which is interrupted by 1 to 6 hetero atoms selected from the group consisting of O, S and N,

R_7 is hydrogen or R_9 ,

R_8 is hydrogen or $\text{C}_1\text{-C}_4\text{alkyl}$, and

R_9 is $\text{C}_1\text{-C}_{12}\text{alkyl}$, $\text{C}_2\text{-C}_{12}\text{alkylene}$, or $\text{C}_3\text{-C}_{12}\text{alkyl}$ which is interrupted by 1 to 6 hetero atoms selected from the group consisting of O, S and N.

Alkyl or alkylene may be straight-chain, branched, monocyclic or polycyclic.

Accordingly, $\text{C}_1\text{-C}_{37}\text{alkyl}$ is, for example, methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, cyclobutyl, n-pentyl, 2-pentyl, 3-pentyl, 2,2-dimethylpropyl, cyclopentyl, cyclohexyl, n-hexyl, n-octyl, 1,1,3,3-tetramethylbutyl, 2-ethylhexyl, nonyl, trimethylcyclohexyl, decyl, menthyl, thujyl, bornyl, 1-adamantyl, 2-adamantyl, dodecyl, tetradecyl, hexadecyl, octadecyl, eicosyl, heneicosyl, docosyl or tetracosyl.

C_1-C_{37} Alkyl is usually preferably methyl, straight-chain $C_{10}-C_{24}$ alkyl or $\begin{array}{c} R_{10} \\ | \\ - \\ | \\ R_{10}' \end{array}$ wherein R_{10}

and R_{10}' are each independently of the other straight-chain $C_{10}-C_{18}$ alkyl. C_1-C_{37} Alkyl is usually

particularly preferably methyl, straight-chain $C_{10}-C_{18}$ alkyl or $\begin{array}{c} R_{10} \\ | \\ - \\ | \\ R_{10}' \end{array}$, wherein R_{10} and R_{10}' are

straight-chain $C_{10}-C_{14}$ alkyl.

C_7-C_{37} Alkylene is mono- or polyunsaturated C_7-C_{37} alkyl.


C_5-C_{16} Alkyl which is interrupted by 1 to 6 hetero atoms selected from the group consisting of O, S and N is typically $-(CH_2CH_2O)_n-R_{11}$, $-(CH_2CH(CH_3)O)_n-R_{11}$, $-(CH_2CH_2N(CH_2CH_2OR_{11})_2$, 2-morpholylethyl or 2-tetrahydropyranyl, wherein n is a number from 1 to 6, and R_{11} is C_1-C_{12} alkyl. In general, interrupting a chain by hetero atoms has substantially the same effect as extending its length by the same number of carbon atoms.

Halogen is typically chloro, bromo or fluoro, preferably chloro.

L is preferably methyl, straight-chain $C_{10}-C_{18}$ alkyl or $\text{---} \langle \text{benzene ring} \rangle \text{---} R_1$, most preferably methyl or straight-chain $C_{10}-C_{18}$ alkyl. If B is C_6-C_{24} alkyl, then L is particularly preferably methyl.

B and D are preferably identical. B and D are particularly preferably straight-chain C_6-C_{10} -

alkyl, $\begin{array}{c} R_{12} \\ | \\ - \\ | \\ R_{12}' \end{array}$, wherein R_{12} and R_{12}' are straight-chain $C_{10}-C_{14}$ alkyl, $\text{---} \langle \text{benzene ring} \rangle \text{---} R_2$ or





wherein R_2 , R_3 , R_4 and R_5 have the meanings cited above.

R_1 is preferably C_6 - C_{12} alkyl.


R_2 is preferably halogen, cyano or nitro, particularly preferably halogen.

R_3 , R_4 or R_5 other than hydrogen is preferably OR_6 , SR_6 , ,



R_6 is preferably straight-chain C_{10} - C_{24} alkyl or , wherein R_{10} and R_{10}' are each

independently of the other straight-chain C_{10} - C_{16} alkyl, particularly preferably straight-chain


C_{10} - C_{18} alkyl or , wherein R_{10} and R_{10}' are straight-chain C_{10} - C_{14} alkyl.

R_7 is preferably C_1 - C_{12} alkyl.



R_8 is preferably hydrogen.

R_{11} is preferably methyl or ethyl.

Compounds of particular interest are 1,4-diketopyrrolo[3,4-c]pyrroles of formula IIa, IIb, IIc or IId,





wherein R_{13} , R_{14} and R_{15} are each independently of one another OR_6 , SR_6 , SeR_6 , $-NHR_5$,




$-\text{CH}=\text{N}-\text{C}_6\text{H}_4-OR_9$, and L , R_6 , R_7 , R_8 and R_9 have the meaning cited above.


Preferred 1,4-diketopyrrolo[3,4-c]pyrroles are those of formula IIa, IIb, IIc or IIId, wherein L is

methyl, straight-chain C_{10} - C_{18} alkyl or $-\text{CO}-\text{C}_6\text{H}_4-R_{16}$, R_6 is straight-chain C_{10} - C_{18} alkyl,


and R_{16} is straight-chain C_6 - C_{12} alkyl and, in particular, those wherein R_{13} , R_{14} and R_{15} are each independently of one another OR_6 , SR_6 , ,  or



The inventive 1,4-diketopyrrolo[3,4-c]pyrroles of formula I, wherein B and D are identical aryl groups, can be prepared in general analogy to commonly known methods, for example by reacting 1 mol of dialkyl succinate with 2 mol of a nitrile of formula




in accordance with the process described in US-4,579,949 to a diketopyrrolopyrrole of formula




which is then reacted with 2 mol of a compound of formula $L-Y$ (V), wherein Y is a leaving group, such as chloro, bromo, iodo or toluenesulfonyl, as is described in US-4,585,878.

The inventive 1,4-diketopyrrolo[3,4-c]pyrroles of formula I, wherein B and D are different groups or identical alkyl groups, can be prepared in general analogy to commonly known methods, for example by reacting a pyrrolinone of formula



with a nitrile of formula D-CN (VII) at a molar ratio of 1:1 in accordance with the process described in US-4,659,775 to a diketopyrrolopyrrole of formula



which is then reacted with 2 mol of a compound of formula L-Y (V), as is described in US-4,585,878.

The compounds of formula III, V, VI and VII are compounds which are known per se. Should any of them still be novel they can be prepared by generally known methods.

Surprisingly, the novel 1,4-diketopyrrolo[3,4-c]pyrroles meet the demands placed on the liquid crystalline compounds with the additional advantage that they have inherent colour which, depending on the structure (in particular depending on groups B and D), can range from yellow to orange, red and blueish red. They are therefore excellently suitable for the manufacture of optical devices having liquid crystalline properties, no admixture of additional colourants being required. Accordingly, this invention also relates to the use of a compound of formula I for the manufacture of optical devices having liquid crystalline properties.

Optical devices having liquid crystalline properties are, for example, liquid crystalline displays which, depending on the applied electrical voltage, have different colours or may also be

colourless. Preferred liquid crystalline displays are those, wherein a great number of points or segments can be controlled individually, i.e. screens. Liquid crystalline colour screens are particularly preferred.

Accordingly, this invention also relates to an optical device having liquid crystalline properties, which comprises a compound of formula I.

The inventive compounds of formula I can be used singly. However, they can also be used in mixtures with other compounds of formula I, for example as binary or ternary mixtures. It is also possible, however, to combine the novel compounds of formula I as components with compounds of different chemical structure which are known to have a liquid crystalline state. By mixing different liquid crystalline compounds with each other and/or with additives known per se, the physical properties of the liquid crystalline phase can be influenced, in particular the order parameter, the viscosity and the temperature range in which liquid crystallinity occurs. The inventive compounds of formula I can be used in mixtures even in cases where the pure compounds of formula I do not clearly show a liquid crystalline state.

This invention therefore also relates to a liquid crystalline phase, comprising 0.1 to 100% by weight, based on the entire liquid crystalline phase, of a compound of formula I. The liquid crystalline phase preferably comprises at least 1% by weight, particularly preferably at least 10% by weight, very particularly preferably at least 40% by weight, based on the entire liquid crystalline phase, of a compound of formula I. The liquid crystalline phase most preferably consists essentially of 1 to 3 liquid crystalline components.

The inventive compounds are also excellently suited as liquid crystal dyes for improving the colour contrast of known, coloured or preferably colourless liquid crystals. The resulting coloured liquid crystalline phases have improved properties, as compared with liquid crystalline phases coloured by known liquid crystal dyes [see P. Gregory, High Technology Applications of Organic Colorants, Chapter 1 (Plenum Press, New York & London 1991), and therein cited references)]; especially the order parameter and the light stability are high.

Depending on the structure, in particular on the length of L, on the degree of branching of B and D, and/or on the nature of R₁₃, R₁₄ and R₁₅ in formulae IIa to IIId, the inventive liquid

crystalline compounds of formula I are calamitic or discotic liquid crystals. Calamitic liquid crystals are promoted by short L (for example methyl) and/or in particular by rectilinear and unbranched B and D (for example 4-(n-decyloxy)phenyl or (4'-alkoxy-biphenyl)-4-yl). Calamitic liquid crystals are preferably of formula IIa, IIb or IIc, wherein L is methyl and/or R_{14} is unsubstituted and/or substituted biphenyl-4-yl. Discotic liquid crystals on the other hand are promoted by long L (for example straight-chain dodecyl) and/or in particular by highly branched B and D (for example 3,4,5-tri(n-decyloxy)phenyl). Discotic liquid crystals are preferably of formula IIa, IIb or IIc, wherein L is C_{10} - C_{18} alkyl and/or R_{13} and R_{15} are OR_6 , SR_6 , NHR_6 or NR_6R_7 .

Depending on the structure and temperature, a columnar, nematic or smectic mesophase may be found. Preferred liquid crystalline compounds are those of formula I having a nematic phase, particularly preferably a nematic as well as a smectic phase. Those liquid crystalline compounds are preferred which have a high enthalpy change upon transition from the crystalline to the liquid crystalline state.

The following examples illustrate the invention. Unless otherwise stated, alkyl is n-alkyl and the assignment of the mesophase is not always clear:

Example 1 : a) A solution consisting of 77.55 g (0.3 mol) of 1-hexadecanethiol in 50 ml of N,N-dimethylacetamide is added, with stirring, to a suspension consisting of 41.27 g (0.3 mol) of 4-chlorobenzonitrile and 58.05 g (0.42 mol) of potassium carbonate (anhydrous) in 200 ml of N,N-dimethylacetamide. After heating this mixture under nitrogen to 120°C, it is stirred for 18 hours at this temperature and then cooled to room temperature and charged with 1 l of water. The mixture is then filtered and the filtrate is washed with water until it is neutral. The product is dried at 60°C/160 mbar.

107.1 g (99.3% of theory) of 4-(hexadecylthio)benzonitrile (white powder) are obtained.


<u>Analysis:</u>	C	H	N	S
calcd.:	76.82%	10.36%	3.89%	9.22%
found:	76.71%	10.52%	4.08%	8.84%

b): Under nitrogen, 100.69 g (0.28 mol) of 4-(hexadecylthio)benzonitrile (Example 1a) are

added at 90°C to a sodium tert-amylate solution, which is prepared from 9.66 g (0.42 mol) of sodium and 400 ml of t-amyl alcohol. With stirring, 28.32 g (0.14 mol) of diisopropyl succinate are then added over 6 hours at 102°C. The reaction mixture is stirred at 102°C for another 16 hours and is then cooled to room temperature and forced into a mixture of 500 ml of water and 500 ml of methanol. This mixture is filtered and the filter product is washed with methanol and then with water. After drying at 80°C/160 mbar, 99.93 g (89.1% of theory) of a dark red product are obtained.

<u>Analysis:</u>	C	H	N	S
calcd.:	74.95%	9.56%	3.50%	8.00%
found:	75.11%	9.78%	3.63%	8.11%

c): Under nitrogen, 9.62 g (0.012 mol) of the product of example 1b are added in small portions over 1 hour to a suspension consisting of 1.92 g (0.048 mol) of sodium hydride (60% dispersion in oil) in 200 ml of 1-methyl-2-pyrrolidone (dried over a molecular sieve). The reaction mixture is stirred for 1 hour at room temperature. With vigorous stirring, 6.81 g (0.048 mol) of methyl iodide are added dropwise to the solution so obtained. Stirring is continued for 50 hours and the mixture is then charged with 500 ml of an ice/water mixture and subsequently with 50 ml of ethyl acetate. The mixture is filtered and the filter product is rinsed with 2 x 20 ml of ethyl acetate. After extraction in a Soxhlet apparatus with 400 ml of dichloromethane, the extract is concentrated by evaporation and the residue is dried at 60°C/160 mbar, giving 3.73 g (37.5% of theory) of a red product of formula



Analysis:	C	H	N	S
calcd.:	75.31%	9.72%	3.38%	7.73%
found:	75.14%	9.97%	3.53%	7.55%

The phase transition is determined by DSC. The texture of the mesophase is also seen under a polarising optical microscope:

cr. = 90°C (crystalline melting point: crystalline phase → liquid crystalline phase)

c.p. = 114°C (clearing point: liquid crystalline phase → isotropic liquid phase).

The liquid crystalline mesophase of this substance exists in the range of 90-114°C.


Example 2 : a) A suspension consisting of 75.66 g (0.55 mol) of 4-chlorobenzonitrile, 106.42 g (0.77 mol) of potassium carbonate and 111.32 g (0.55 mol) of 1-dodecanethiol is heated, with stirring, under an inert gas atmosphere in 280 ml of N,N-dimethylacetamide to 130°C and is then stirred at this temperature for 24 hours. After cooling the reaction mixture to room temperature, it is poured on a mixture of 700 g of ice and 750 ml of water. The mixture is filtered and the filter cake is washed with water. The product is recrystallised from methanol and dried at 50°C under vacuum, affording 160.2 g (96% of theory) of 4-(dodecylthio)benzonitrile.

Analysis:	C	H	N	S
calcd.:	75.19%	9.63%	4.62%	10.56%
found:	74.86%	9.80%	4.46%	10.52%

b): Under nitrogen, 13.79 g (0.6 mol) of sodium are added to 400 ml of dry tert-amyl alcohol and this mixture is heated to 102°C. With vigorous stirring, the melted sodium is kept for 16 hours at 102°C. After cooling the resulting solution to 90°C, 121.4 g (0.4 mol) of 4-(dodecylthio)benzonitrile (of example 2a) are added. With stirring, 40.45 g (0.2 mol) of diisopropyl succinate are added to this mixture over 5½ hours at 102°C. The reaction mixture is stirred at 102°C for another 18 hours and is then cooled to room temperature and added to a mixture of 750 ml of methanol and 750 ml of water. The red suspension is filtered and washed first with methanol and then with water. The product is dried at 80°C under vacuum, giving 86.3 g (62.6% of theory) of a dark red powder.

<u>Analysis:</u>	C	H	N	S
calcd.:	73.21%	8.78%	4.07%	9.31%
found:	73.46%	8.75%	3.98%	9.49%

c): Under nitrogen, 1.72 g (0.0025 mol) of the product of example 2b) are added to a suspension consisting of 0.40 g (0.010 mol) of sodium hydride (60% dispersion in oil) in 20 ml of 1-methyl-2-pyrrolidone (dried over a molecular sieve). After stirring this mixture for 1½ hours at room temperature, 1.42 g (0.010 mol) of methyl iodide are added dropwise and the reaction mixture is stirred for another 22 hours. Subsequently, the reaction mixture is poured on 100 ml of an ice/water mixture. 5 ml of ethyl acetate are added to the resulting emulsion. This mixture is filtered and the filter cake is washed with a small amount of ethyl acetate (about 5 ml). After a Soxhlet extraction with 300 ml of ethyl acetate, the solvent is stripped off under vacuum and the residue is dried at 60°C under vacuum, affording 1.22 g (68% of theory) of a red product of formula



<u>Analysis:</u>	C	H	N	S
calcd.:	73.69%	9.00%	3.91%	8.94%
found:	73.56%	9.00%	3.90%	8.74%

The liquid crystalline mesophase of this substance exists in the range of 104-114°C.


Example 3 : a) Under nitrogen, a mixture consisting of 64.7 g (0.26 mol) of diethyl maleate and 0.4 g of dibenzoyl peroxide is added dropwise over 12½ hours to 104.9 g (0.81 mol) of caprylic aldehyde at 80°C. The reaction is completed by heating to 80°C under nitrogen for

52 hours, adding another 0.4 g of dibenzoylperoxide in two equal portions. The reaction mixture is then cooled to room temperature, washed with saturated aqueous sodium carbonate solution and then dried over anhydrous magnesium sulfate. Fractional distillation affords 65.9 g (83% of theory) of diethyl α -octanoylsuccinate.

Melting point: 138-142°C / 0.05 mbar.

<u>Analysis:</u>	C	H
calcd.:	63.97%	9.40%
found:	64.28%	9.58%

b) 70.1 g of the product of example 3a) are added, with vigorous stirring, to a solution consisting of 137.5 g of ammonium acetate in 400 ml of acetic acid at 60°C. After stirring this mixture for another 20 hours under nitrogen at 100°C, it is cooled to room temperature and mixed with 600 ml of water. After extracting the resulting product with 300 ml of ethyl acetate, it is washed first with saturated aqueous sodium hydrogencarbonate solution and then with water and is subsequently dried over anhydrous magnesium sulphate. Purification by column chromatography gives 40.7 g (76.5% of theory) of a solid substance of formula




<u>Analysis:</u>	C	H	N
calcd.:	66.37%	9.15%	5.53%
found:	64.73%	9.21%	5.11%

c) 50.09 g of caprylic acid nitrile are added at 90°C under nitrogen to a sodium tert-amylate solution obtained from 6.9 g of sodium and 300 ml of tert-amyl alcohol. 25.33 g of the product of example 3b) are then added in portions to this mixture over 80 minutes at 80°C and the reaction mixture is then stirred for 20 hours at reflux. After cooling the mixture to room temperature, it is mixed with 350 ml of water, 350 ml of methanol and 29.56 g of 37% hydrochloric acid and is then filtered. The residue is washed with water and dried at 80°C / 160 mbar, giving 9.16 g (27.5% of theory) of a yellow product of formula



<u>Analysis:</u>	C	H	N
calcd.:	72.25%	9.70%	8.43%
found:	72.11%	9.83%	8.39%

d) Under nitrogen; 3.99 g of the product of example 3c) are added in small portions at room temperature over 2½ hours to a suspension consisting of 1.92 g of sodium hydride in 60 ml of 1-methyl-2-pyrrolidinone. This mixture is stirred for 1 hour and then 6.81 g of methyl iodide are added dropwise over 50 minutes. After stirring the resulting suspension for 18 hours at room temperature under nitrogen, it is mixed with 120 ml of ice-cold water and extracted with ethyl acetate. The extraction product is dried over anhydrous magnesium sulphate and is then concentrated to dryness by evaporation. Purification of the remaining brown viscous liquid by column chromatography gives a yellow viscous product of formula




MS (EI): m/e 360 (M⁺); c.p.: 66°C.

The liquid crystalline mesophase of this substance exists in the range of about 10 to 66°C. The SB mosaic texture of the mesophase is also seen under a polarising optical microscope.


Examples 4-8 : A procedure analogous to that of examples 1 and 2 gives the following homologous compounds having liquid crystalline properties:

Example	R ₁₇
4	C ₈ H ₁₇
5	C ₉ H ₁₉
6	C ₁₀ H ₂₁
7	C ₁₄ H ₂₉
8	C ₁₈ H ₃₇




Examples 9-16 : A procedure analogous to that of examples 1 and 2 gives the following homologous compounds having liquid crystalline properties:

Example	R ₁₇	R ₁₈
9	C ₈ H ₁₇	C ₁₂ H ₂₅
10	C ₉ H ₁₉	C ₁₂ H ₂₅
11	C ₁₀ H ₂₁	C ₁₆ H ₃₃
12	C ₁₂ H ₂₅	C ₁₂ H ₂₅
13	C ₁₂ H ₂₅	C ₁₆ H ₃₃
14	C ₁₄ H ₂₉	C ₁₈ H ₃₇
15	C ₁₆ H ₃₃	C ₁₈ H ₃₇
16	C ₁₈ H ₃₇	C ₁₈ H ₃₇




Example 17 : a) 4.0 g of sodium are stirred in 200 ml of tert-amyl alcohol at reflux temperature until the reaction is complete. After cooling to 90°C, 51.94 g of 3,4-di-decylthiobenzonitrile are added, followed by the dropwise addition of 11.73 g of diisopropyl succinate. The resulting violet coloured reaction mixture is heated to reflux and stirred overnight. It is then cooled to room temperature, transferred to a well-stirred water-methanol mixture and stirred for a further 4 hours. The crude product is collected by filtration and

reslurried in a methanol-ethyl acetate mixture. The resultant product crystals are filtrated, washed with methanol and dried at 50°C / 160 mbar, affording 28.27 g (49.8% of theory) of the compound of formula



<u>Analysis:</u>	C	H	N	S
calculated:	71.26%	9.48%	2.87%	13.12%
found:	70.89%	9.54%	2.91%	13.12%


b): 24.44 g of the product of example 17a) are added, in small portions, to a well stirred mixture of 4.0 g of sodium hydride (60% dispersion in mineral oil) and 300 ml of 1-methyl-2-pyrrolidinone under nitrogen atmosphere. After stirring for 75 minutes, 14.19 g of methyl iodide is added, and the reaction is allowed to proceed at room temperature overnight. The mixture is then poured into an ice-water mixture, the precipitated product is filtered off, washed with water and dried at 50°C under vacuum. The crude product is recrystallised from ethyl acetate to yield 11.06 g (44% of theory) of a bright red coloured crystalline product of the formula



Analysis:	C	H	N	S
calculated:	71.66%	9.62%	2.79%	12.75%
found:	71.70%	9.61%	2.85%	12.83%


$^1\text{H-NMR}(\text{CDCl}_3)$: 7.88 (s, 2H); 7.69 (d, 2H); 7.30 (d, 2H); 3.37 (s, 6H); 3.07-2.97 (m, 8H); 1.78-1.67 (m, 8H); 1.53-1.40 (m, 8H); 1.35-1.20 (m, 48H); 0.91-0.84 (m, 12H).

Example 18 : a) A suspension of 122.80 g of 4-hydroxybenzonitrile in 458 ml of 3,4-dihydro-2H-pyran is stirred at reflux temperature for 72 hours, after which the excess of the solvent is evaporated off under reduced pressure. The resultant yellow coloured oil is purified by flash column chromatography (silica gel, n-hexane / ethyl acetate, 9:1) to yield 179.05 g (88.1% of theory) of a colourless crystalline compound of the formula




Analysis:	C	H	N
calculated:	70.92	6.45	6.89
found:	70.91	6.72	6.74

b): Under nitrogen atmosphere, 89.43 g of the product of example 18a) are added to a sodium tert-amyl alcohol solution heated to 90°C, followed by the dropwise addition of 53.40 g of diisopropyl succinate over 1½ hours. The reaction mixture is stirred for 24 hours under reflux and then cooled down to room temperature. It is transferred to a water-methanol mixture, and the resultant red mixture heated to 60°C and stirred at this temperature for 4½ hours. The solid is collected by filtration, washed with water and dried at 80°C under vacuum, affording 12.25 g (11.4% of theory) of the compound of formula




Analysis:	C	H	N
calculated:	68.84%	5.78%	5.73%
found:	68.15%	6.05%	5.72%

c): A mixture of 48.85 g of the product of example 18b), 1 l of ethanol, 63 ml of water and 5.6 ml of concentrated sulphuric acid is heated and stirred at reflux for 25 hours. After cooling to room temperature, the precipitated product is collected by filtration, washed with ethanol and water and dried at 80°C under vacuum, affording 20 g (62.5% of theory) of the product of formula




Analysis:	C	H	N
calculated:	67.50%	3.78%	8.75%
found:	63.89%	4.08%	8.33%

d): 9.61 g of the product of example 18c) are added in small portions to a well stirred mixture of 9.6 g of sodium hydride (60% dispersion in mineral oil) and 200 ml of 1-methyl-2-pyrrolidinone under nitrogen atmosphere. After stirring for 1 hour, 71.10 g of 1-iodododecane are added during a period of 30 minutes, and the reaction is allowed to proceed at room temperature for 27½ hours. The reaction mixture is diluted with 500 ml of water, and the product isolated by filtration, recrystallised from ethyl acetate to yield 6.40 g (21.5% of theory) of the compound of formula




Analysis:	C	H	N
calculated:	79.78%	10.96%	2.82%
found:	79.67%	10.82%	2.78%

Example 19 : a) A sodium tert-amylate solution is prepared by reacting 10.12 g of sodium with 450 ml of tert-amyl alcohol at reflux temperature overnight. It is then cooled to 90°C and 63.24 g of 4-dodecyloxybenzonitrile are added, followed by the dropwise addition of 22.24 g of diisopropyl succinate over 5 hours. The reaction mixture is stirred for 21 hours under reflux and then allowed to cool down to room temperature. It is transferred into a water-methanol mixture and the precipitated product collected by filtration, rinsed with methanol and water, and dried at 80°C under vacuum. This affords 6.90 g (9.55% of theory) of the compound of formula



Analysis:	C	H	N
calculated:	76.79%	9.21%	4.26%
found:	76.24%	8.96%	4.11%

b): 9.85 g of the compound from example 19a) are added to a mixture of 2.40 g of sodium hydride (60% dispersion in mineral oil) in 200 ml of 1-methyl-2-pyrrolidinone, under nitrogen atmosphere, and the mixture is stirred at room temperature for 1½ hours, resulting in a violet coloured solution. 8.52 g of iodomethane are added portionwise to this well-stirred solution, and the suspension is stirred at ambient temperature for 24 hours. It is then poured into an ice-water mixture, the precipitated product is isolated by filtration, washed with water and dried at 80°C under vacuum, affording 9.76 g of the compound of formula




A crystalline sample is obtained by recrystallisation from ethyl acetate.


Analysis:	C	H	N
calculated:	77.15%	9.42%	4.09%
found:	76.87%	9.48%	4.10%

Examples 20-29: A procedure analogous to that of example 19 gives the following homologous compounds having liquid crystalline properties:

Example	R ₁₉	R ₂₀
20	C ₇ H ₁₅	CH ₃
21	C ₉ H ₁₉	CH ₃
22	C ₁₀ H ₂₁	CH ₃
23	p-H ₅ C ₂ OC ₂ H ₄ OC ₆ H ₄ -	CH ₃
24	p-H ₂₁ C ₁₀ C ₆ H ₄ -	CH ₃
25	C ₇ H ₁₅	C ₁₀ H ₂₁
26	C ₉ H ₁₉	C ₁₀ H ₂₁
27	C ₉ H ₁₉	C ₁₂ H ₂₅
28	C ₁₂ H ₂₅	C ₁₂ H ₂₅
29	C ₁₂ H ₂₅	C ₁₈ H ₃₃




Example 30 : a) An aqueous sodium hydroxide solution (2.24 g in 20 ml water) is added to a solution of 10.0 g of 4'-hydroxy-4-biphenylcarbonitrile in 250 ml ethanol at 50°C, under nitrogen atmosphere, followed by 28.3 g of 1-bromodecane added dropwise over 20 minutes. The resulting yellow coloured suspension is stirred at 60°C for 26 hours, then chilled in an ice bath. The precipitate is collected by filtration, rinsed with cold ethanol and dried at 30°C under vacuum. This yields 12.48 g (72.9% of theory) of a white crystalline compound of the formula




Analysis:	C	H	N
calculated:	82.34%	9.71%	4.18%
found:	82.35%	8.52%	4.08%

b): Under nitrogen atmosphere, 12.18 g of the product of example 30a) are added to a sodium tert-amyl alcohol solution heated to 100°C, followed by the dropwise addition of 3.67 g of diisopropyl succinate. The reaction mixture is stirred for 16 hours under reflux, then cooled to room temperature and transferred to a mixture containing 250 ml of methanol, 9 ml of acetic acid and 150 ml of tert-amyl alcohol. The resultant suspension is stirred at ambient temperature for 3 hours. The product is collected by filtration, washed with methanol, then with water, and dried at 80°C under vacuum, affording 8.42 g (61.6% of theory) of the compound of formula



Analysis:	C	H	N
calculated:	79.75%	8.03%	3.72%
found:	79.01%	7.97%	3.47%

c): 8.28 g of the product of example 30b) and 25 ml of tert-amyl alcohol are added under nitrogen atmosphere to a sodium tert-amylate solution (prepared with 0.56 g sodium and 80 ml tert-amyl alcohol) at 100°C. The mixture is stirred for 2 hours at the reflux temperature, then cooled to room temperature, and 3.88 g of dimethyl sulphate are added portionwise over a period of 30 minutes. The resulting mixture is stirred at room temperature for 48 hours during which 1.94 g more dimethyl sulphate is added. The product is collected by filtration, washed with methanol and dried under vacuum. The crude product is extracted into methylene chloride in a Soxhlet, and the extract is evaporated to dryness. Recrystallization from ethyl acetate affords 3.77 g (43.9%) of the compound of formula




Analysis:	C	H	N
calculated:	79.96%	8.26%	3.59%
found:	79.48%	8.27%	3.48%

Melting point 139.3°C; clearing point 302.9°C.

Under an optical polarizing microscope, the Schlieren texture of the nematic mesophase is observed.


Example 31 : Following the synthetic procedure described in example 30, the following liquid crystalline compound is obtained by using 1-iodohexadecane instead of 1-bromodecane:




Analysis:	C	H	N
calculated:	80.97%	9.34%	2.95%
found:	80.96%	9.44%	2.81%

Melting point 115.8°C; clearing point 234.5°C. Under an optical polarizing microscope, the Schlieren texture of the nematic mesophase is observed.

Example 32 : a) The general procedure of example 18a) is repeated, but replacing 4-hydroxybenzonitrile with 3,5-dihydroxybenzonitrile. The following compound is obtained:




b): Following the synthetic procedure described in example 18b) but using the benzonitrile from example 32a) instead, the following compound is obtained:




Analysis:	C	H	N
calculated:	66.26%	6.44%	4.07%
found:	65.52%	6.51%	4.08%

c): The general procedure of example 19b) is repeated, using the product of example 32b) instead of that of example 19a), and replacing iodomethane with 1-iododecane. The following compound is obtained:




The ¹H-NMR spectrum confirms the structure.

Example 33 : a) The product of example 32c) is subjected to acid hydrolysis following the general procedure analogous to example 18c), yielding the following compound:



The $^1\text{H-NMR}$ spectrum is in full agreement with the structure.


b): The general procedure of example 18d) is repeated, but using the product of example 33a) instead of that of example 18c), and replacing 1-iodododecane with 1-iodoheptane, giving the following compound having liquid crystalline properties:



<u>Analysis:</u>	C	H	N
calculated:	77.29%	10.61%	2.73%
found:	77.00%	11.20%	2.32%

Example 34 : a) 53 g of 4-cyanobenzaldehyde, 34.5 ml of 1,3-propanediol, 9.19 g of tosyl acid and 1 l benzene are placed in a flask equipped with a stirrer and a Dean-Stark separator


fitted with a condensor. The mixture is stirred under reflux for 5 hours, during which approximately 7 ml of water are collected in the trap. The resulting mixture is cooled to room temperature and extracted first with a 2% aqueous sodium hydrogencarbonate solution (2 x 500 ml), and then with distilled water (2 x 500 ml). The organic phase is dried over MgSO_4 . The solvent is removed under reduced pressure and the solid dried under vacuum at 60°C . 68.2 g (90.1% of theoretical) of the following compound are obtained:



The white crystalline solid has a melting point of $108-109^\circ\text{C}$.


Analysis:	C	H	N
calculated:	69.83%	5.86%	7.40%
found:	69.88%	5.87%	7.10%

b): 37.8 g of the product of example 34a), followed by 20.2 g of di-isopropyl succinate, are added to a sodium tert-amylate solution, obtained from 6.90 g of sodium and 600 ml of tert-amyl alcohol, under nitrogen. After heating up to 100°C , the reaction is allowed to continue at this temperature for 28 hours. After that, the mixture is cooled to room temperature and poured into a mixture of 45 ml acetic acid and 1400 ml methanol. The fine crystalline product is collected by filtration, washed with methanol followed by water, and dried under vacuum at 80°C . This yields 18.0 g (39% of the theoretical) of a dark red solid product with the following structure:




Analysis:	C	H	N
calculated:	67.82%	5.25%	6.08%
found:	67.71%	5.29%	6.07%

c): A suspension of 6.70 g of the product of example 34b), 300 ml of a 2M aqueous hydrochloric acid solution and 350 ml of tetrahydrofuran is stirred under reflux for 70 hours and then cooled to room temperature. The dark red product is collected by filtration, washed with methanol and water, and dried under vacuum at 60°C. This yields 4.86 g (97% of the theoretical) of a product with the following structure:




Analysis:	C	H	N
calculated:	69.76%	3.51%	8.14%
found:	68.58%	3.66%	8.09%

d): A mixture of 1.00 g of the product of example 34c), 1.54 g of p-octyloxyaniline, 0.08 g of p-tosyl acid and 50 ml of methyl sulfoxide is stirred at 110°C for 3 hours. It is then cooled to ambient temperature and left overnight. The solid product is collected by filtration, washed with methanol and water, and dried under vacuum at 60°C, yielding 1.94 g (89% of the theory) of a dark red crystalline compound of the formula:




Analysis:	C	H	N
calculated:	76.77%	7.25%	7.46%
found:	76.01%	7.06%	7.56%

e): The general procedure of example 19b) is repeated, but using the product of example 34d) instead of that of example 19a), yielding the following compound with liquid crystalline properties:



Analysis:	C	H	N
calculated:	77.09%	7.50%	7.19%
found:	76.38%	7.30%	7.27%

Example 35 : a) The general procedure of example 34a) is repeated, but replacing 1,3-propanediol with 1,2-tetradecanediol, giving the following compound:




Analysis:	C	H	N
calculated:	76.92%	9.68%	4.08%
found:	76.37%	10.07%	3.49%

b): The general procedure of example 34b) is repeated, but using the benzonitrile from example 35a) instead of that from example 34a). A dark red product is obtained.


Analysis:	C	H	N
calculated:	74.96%	8.91%	3.64%
found:	74.89%	9.09%	3.39%

c): The general procedure of example 19b) is followed, using the product of example 35b) instead of that of example 19a), yielding the following compound useful in liquid crystalline compositions:














Examples 36-40 : A procedure analogous to that of example 3 gives the following homologous compounds having liquid crystalline properties:

Example	R ₂₁	R ₂₂	R ₂₃
36	C ₇ H ₁₅	C ₇ H ₁₅	C ₇ H ₁₅
37	C ₆ H ₁₃	CH ₃	p-Cl-C ₆ H ₄ -
38	C ₆ H ₁₃	C ₆ H ₁₃	p-Cl-C ₆ H ₄ -
39	C ₇ H ₁₅	CH ₃	p-Cl-C ₆ H ₄ -
40	C ₇ H ₁₅	C ₇ H ₁₅	p-Cl-C ₆ H ₄ -



Examples 41-49 : Following the procedure of the above examples, or in close analogous thereto, one obtains the following compounds of formula IIc having liquid crystalline properties observable under a polarising optical microscope:


Ex.	R ₁₄	L	cr. [°C]	[kJ/mol]	mesophase	c.p. [°C]
19	OC ₁₂ H ₂₅	CH ₃	108	82	smectic A	122
22	OC ₁₀ H ₂₁	CH ₃	106	69	smectic A	118
41	OC ₈ H ₁₇	CH ₃	106	59	nematic	114
42	 OC ₆ H ₁₃	CH ₃	205	44	nematic	336
43	 C ₄ H ₉	CH ₃	220	4	nematic	331
44	 C ₃ H ₇	CH ₃	190	23	nematic	357
45	 -  C ₅ H ₁₁	CH ₃	248	31	nematic	327
46	 -  C ₅ H ₁₁	C ₂ H ₅	243	38	nematic	348
47	 -  C ₅ H ₁₁	C ₃ H ₇	210	36	nematic	337
48	 C ₅ H ₁₁	CH ₃	182	20	LC range narrow	
49	 OC ₁₄ H ₂₉	CH ₃	137	32	smectic	280

Examples 50-52 : A procedure analogous to that of the above examples gives the compounds of formula IIa having liquid crystalline properties, which compounds are observed under the polarisation microscope at rising temperature:

Ex.	$R_{13} = R_{14} = R_{15}$	L	cr. [°C]	[kJ/mol]	mesophase ^(†)	c.p. [°C]
50	OC ₆ H ₁₃	CH ₃	117	36	columnar	146
51	OC ₈ H ₁₇	CH ₃	83	32	columnar	129
52	OC ₁₀ H ₂₁	CH ₃	65	45	columnar	114


^(t) these mesophases may also be smectic instead of columnar.

Example 53 : A binary mixture of the compounds of examples 41 and 46 (1 : 1 by weight) exhibits liquid crystalline properties observable under the polarising optical microscope:

Ex.	R ₁₄	L	cr. [°C]	[kJ/mol]	mesophase ^(†)	c.p. [°C]
53		CH ₃ CH ₃	138	19	nematic	280


^(†) this mesophase may also be smectic instead of nematic.

Example 54 : A binary mixture of the compound of example 41 and the compound of formula




which is prepared according to the above examples (3 : 1 by weight), exhibits liquid crystalline properties.

Example 55 : A binary mixture of the compound of example 41 and the compound of formula


IIc, wherein L is methyl and R₁₄ is , which is prepared in analogy thereto, (3 : 1 by weight), exhibits liquid crystalline properties.

Example 56 : 5% by weight of the compound of example 12 are mixed with 95% by weight of the liquid crystalline compound of formula



The binary mixture's colour contrast and order parameter are high.


Example 57 : 5% by weight of the compound of example 12 are mixed with 95% by weight of the liquid crystalline compound (NBBA) of formula



The binary mixture's colour contrast and order parameter are high.


What is claimed is

1. A compound of formula



wherein

B and D are each independently of the other C₆-C₂₄alkyl, or





L is -CO-, , , or


C₁-C₃₇alkyl,

R₁ is C₄-C₁₈alkyl,

R₂ is hydrogen, C₁C₄-alkyl, C₁-C₄alkoxy, halogen, cyano or nitro,

R₃, R₄ and R₅ are each independently of one another hydrogen, OR₆, SR₆, SeR₆, -NHR₆,





with the proviso that at least one of R_3 , R_4 and R_5 is not hydrogen,

R_6 is $\text{C}_7\text{-C}_{37}$ alkyl, $\text{C}_7\text{-C}_{37}$ alkylene, or $\text{C}_5\text{-C}_{18}$ alkyl which is interrupted by 1 to 6 hetero atoms selected from the group consisting of O, S and N,

R_7 is hydrogen or R_9 ,

R_8 is hydrogen or $\text{C}_1\text{-C}_4$ alkyl, and



R_9 is $\text{C}_1\text{-C}_{12}$ alkyl, $\text{C}_2\text{-C}_{12}$ alkylene, or $\text{C}_3\text{-C}_{12}$ alkyl which is interrupted by 1 to 6 hetero atoms which are selected from the group consisting of O, S and N.

2. A compound of formula I according to claim 1, wherein L is methyl, straight-chain $\text{C}_{10}\text{-C}_{18}$ alkyl or $-\text{C}_6\text{H}_4-\text{R}_1$, and R_1 is $\text{C}_6\text{-C}_{12}$ alkyl.


3. A compound of formula I according to claim 1, wherein B is $\text{C}_6\text{-C}_{24}$ alkyl and L is methyl.

4. A compound of formula I according to claim 1, wherein B and D are identical.

5. A compound of formula I according to claim 1, wherein B and D are straight-chain




6. A compound according to claim 5, wherein B and D are




7. A compound according to claim 6, wherein R_3 , R_4 or R_5 other than hydrogen is OR_6 or SR_6 ,

and R_6 is straight-chain C_{10} - C_{24} alkyl or $\begin{array}{c} R_{10} \\ | \\ -C- \\ | \\ R_{10}' \end{array}$, wherein R_{10} and R_{10}' are each independently of the other straight-chain C_{10} - C_{18} alkyl.


8. A compound according to claim 1 of formula IIa, IIb, IIc or IIId,




(IIa),



(IIb),





(IIc),



(IIId),

wherein R_{13} , R_{14} and R_{15} are each independently of one another OR_6 , SR_6 , SeR_6 , $-NHR_6$,



9. A compound of formula IIa, IIb, IIc or IId according to claim 8, wherein L is methyl, straight-chain $\text{C}_{10}\text{-C}_{18}$ alkyl or -CO- , R_6 is straight-chain $\text{C}_{10}\text{-C}_{18}$ alkyl, and R_{16} is straight-chain $\text{C}_6\text{-C}_{12}$ alkyl.

10. A liquid crystalline phase, comprising 0.1 to 100% by weight, based on the entire liquid crystalline phase, of a compound of formula I as claimed in claim 1.

11. A liquid crystalline phase according to claim 10, which consists essentially of 1 to 3 liquid crystalline components.

12. Use of a compound of formula I according to claim 1 for the manufacture of optical devices having liquid crystalline properties.

13. An optical device having liquid crystalline properties, which comprises a compound of formula I.

14. An optical device according to claim 13, which optical device is a liquid crystalline display.

15. An optical device according to claim 14, which optical device is a liquid crystalline colour screen.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/06641

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C07D487/04 C09K19/34 //(C07D487/04,209:00,209:00)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07D C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EDMAN P ET AL: "Polarized Light Spectroscopy of Dihydropyrrolopyrroledione in Liquids and Liquid Crystals: Molecular Conformation and Influence by an Anisotropic Environment" J. PHYS. CHEM. (JPCHAX,00223654);95; VOL.99 (21); PP.8504-9, UNIVERSITY OF UMEA;DEPARTMENT OF PHYSICAL CHEMISTRY; UMEA; S-901 87; SWED. (SE), XP002061153 see the whole document --- -/--	1-15

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

2 April 1998

Date of mailing of the international search report

21/04/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Beslier, L

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 97/06641

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	C. PIECHOCKI: "Discotic mesophases obtained from substituted metallophthalocyanines." JOURNAL OF THE AMERICAN CHEMICAL SOCIETY., vol. 104, no. 19, 1982, DC US, pages 5245-5247, XP002061154 cited in the application see the whole document -----	1-15
A	US 4 585 878 A (MAX JOST) 29 April 1986 cited in the application -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 97/06641

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4585878 A	29-04-86	CA 1230341 A	15-12-87
		EP 0133156 A	13-02-85
		JP 1758542 C	20-05-93
		JP 4042431 B	13-07-92
		JP 60035056 A	22-02-85
		US 4666455 A	19-05-87
<hr/>			